L'ANTIC COLONIAL

Model: AC6 NATURAL 1L YUKON

Codes: 100244121 Group: G-213

Format: 19,3X128,2X0,8



COMPOSITION					
		Size	Material	Type of material	
	Layer 1		Overlay	Heavy-duty protecting layer.	
	Layer 2		Decorative.	Especially soaked.	
	Layer 3		Base board.		
	Layer 4		Backside	Shrinkage laminate.	

CERTIFICATIONS

CARB: Phase II compliant Carb certification

ADDITIONAL NOTES

High resistance to water and moisture as long as the instructions for installation of this product for these cases are followed.

FEATURES



Imitates the surface of wood



Gloss-free



25 year warranty for domestic use valid for laminate floors that have been installed in rooms where they are exposed to normal wear and tear for their recommended End Use Category in accordance with EN 13329.



Format where only one board has been used to finish the entire base surface



Floor capable of dissipating excess electrical charges and distribute them over its



It is one of the easiest to install and safest systems in the market. We just need to adjust the board to be installed longitudinally to the one already placed, by applying a soft pressure without the need for any type of tool. Both pieces will fit and will be secured thaple to the order to the first tool. and will be secured thanks to the safety tab. It is just as simple to take apart, which makes for a quick disassembly



33. Intensive commercial



Suitable for bathroom and kitchen floors for residential use, provided that the



Beveled cut on all 4 edges of the board for emphasizing size



Installation system where gluing the boards to the floor is not necessary. They are placed on a foam, joined together, as long as the product does not already have a foil on the back of the piece.



5 year warranty for commercial use valid for laminate floors that have been installed in rooms where they are exposed to normal wear and tear for their recommended End Use Category in accordance with EN 13329.



Is suitable for installing on water radiant heating



 $\label{parameters} Pan European\ Forest\ Certification\ that\ guarantees\ to\ consumers\ the\ origin\ of\ the\ products\ from\ sustainably\ managed\ forests$



23. Intensive residential



Abrasion resistance level according to UNE-EN 13329.





It is advisable to follow the installation and maintenance instructions published by L'ANTIC COLONIAL, S.A.U., observing in any case the legal or regulatory requirements that may exist for each area of use. Do not use aggressive cleaning agents, such as acids, or metallic or sharp elements. In public places, this material must comply with the slipperiness requirements of the Spanish Technical Building Code. This document is purely commercial and may not be used in any legal or administrative proceedings, neither as an expert opinion nor as documentary evidence, unless expressly authorized by L'ANTIC COLONIAL, S.A.U.

AC6 NATURAL 11 VIIKON

L'ANTIC COLONIAL

DIMENSIONAL FEATURES					
Item thickness	±0.1 MM	EN 13329*			
Length of face	±0.5 MM	EN 13329*			
Width of face	±0.1 MM	EN 13329*			
Squareness of the item (q)	≤0.20 mm	EN 13329*			
Straightness of face	≤ 0.30 mm/m				
Flatness of item (f)	fw,Cóncavo≤0.50% fw,Convexo≤1%/fl,Cóncavo≤0.15% fl,Convexo≤0.20% MM	EN 13329*			
Joint between items	≤0.20 mm	EN 13329*			
Difference in height among items	≤0.15 mm	EN 13329*			
Dimensional variations related to changes in relative moisture	≤0.90 mm				
Surface stripping	≥ 1.00 N/mm2				

LABORATORY TESTS						
Resistance to abrasion	AC6	UNE EN 13329:2000*				
Impact resistance	≥1000 mm/≥15 N	EN 13329*				
Resistance to staining	Grado≥4	DIN EN 438-2*				
Furniture leg effect	No damage	EN 424*				
Castor chair effect	No damage	EN 425*				
Swelling in thickness	≤8%	EN 13329*				
Resistance to microscratching	Clase 1	DIN ENV 16094*				
Formaldehyde emissions	E1≤0.05 ppm	DIN EN 717-1*				
Slip resistance (pendulum-wet)	CL 1 (29)	UNE 41901*				
Fire resistance	Cfl-S1	DIN EN 13501-1*				
Evaluation of propensity to accumulation of electrostatic charges	≤2 kV	EN 1815*				
Heat resistance	0.065 M2*K/W					
Slip resistance (dcof)	0.60	ANSI A137.1*				
Critical radiant flux	Clase 1	ASTM E 648*				
Smoke density (burning)	<450 Dmc	ASTM E 662*				
Density of the board	950 ±5 KG/M3	UNE EN 323*				
Slip resistance (pendulum-dry)	CL 2 (42)	UNE 41902*				

	PACKING	
Sales units per box	1.979408 M2/BOX	
Sales units per pallet	102.929215 M2/PAL	
Sales units per unit	0.247426 M2/PIECE	
Sale unit	M2	
Base unit	ST	
Sales units per square meter	1 M2	
Net weight	7.747771 KG/M2	
Gross weight	7.961977 KG/M2	

SPECIAL PIECES									
SAP	Description	Group	Boxes	Pallet	Units	SKU	Basic Unit	Net Weight	Gross weight
100228951	IGUALACION NATURAL 1L YUKON 4X270X1	G-155	20 PIECES/BOX	1000 PIECES/PAL	9.26 PIECES/M2	-	-	0.7 KG/PIECES	0.72 KG/PIECES
100228976	MAMPERLAN AC6 NATURAL 1L YUKON 7X120X3	G-163	2 PIECES/BOX	200 PIECES/PAL	11.9 PIECES/M2	-	-	1.58 KG/PIECES	1.64 KG/PIECES
100228964	TRANSICION NATURAL 1L YUKON 4X270X1	G-155	20 PIECES/BOX	1000 PIECES/PAL	9.26 PIECES/M2	-	-	0.7 KG/PIECES	0.72 KG/PIECES
100228922	ZOCALO NATURAL 1L YUKON 8X220X1,5	G-107	14 PIECES/BOX	560 PIECES/PAL	5.68 PIECES/M2	-	-	1.8 KG/PIECES	1.86 KG/PIECES





It is advisable to follow the installation and maintenance instructions published by L'ANTIC COLONIAL, S.A.U., observing in any case the legal or regulatory requirements that may exist for each area of use. Do not use aggressive cleaning agents, such as acids, or metallic or sharp elements. In public places, this material must comply with the slipperiness requirements of the Spanish Technical Building Code. This document is purely commercial and may not be used in any legal or administrative proceedings, neither as an expert opinion nor as documentary evidence, unless expressly authorized by L'ANTIC COLONIAL, S.A.U.

01/03/2023